

Electrical Insulation Materials

Flexiso® GKG FI 16030

Structure: Flexiso® GKG FI 16030 is made of a polyimide film which is laminated on both sides with glass cloth. The used laminating adhesive is high-temperature resistant.

Characteristics: Flexiso® GKG FI 16030 has good mechanical and electrical properties as well as good flexibility in a wide temperature range. The used glass cloth can be compromised and has a good impregnation for impregnating resins.

Application: Flexiso® GKG FI 16030 is used as slot and phase insulation or as layer insulation in low-voltage machines and transformers which have to meet high thermal requirements.

Standard colour: Flexiso® GKG FI 16030 is delivered in white colour.

Delivery Forms: Flexiso® GKG FI 16030 is supplied in rolls (width max. 980 mm) and as reels (from 10 mm wide). Other formats, for example, blanks, die-cut and formed parts are supplied to customer specifications.

Storage conditions: Flexiso® GKG FI 16030 can be stored unlimited under normal conditions (20° C, 50 % rel. air humidity).

Dr. Dietrich Müller GmbH

Flexiso® GKG FI 16030

Properties	Test method	Unit	Value		
Total thickness	IEC-626-2	mm	0.10	0.20	0.25
		%	±15%	±15%	±15%
Film thickness	IEC-626-2	µm	25	25	50
Basis weight	IEC-626-2	g/m ²	100	265	300
			±12%	±12%	±12%
Yield		m ² /kg	10.0	3.8	3.3
Tensile strength:					
MD	IEC-626-2	N/mm ²	≥85	≥200	≥250
CD	IEC-626-2	N/mm ²	≥80	≥250	≥220
Elongation					
MD	IEC-626-2	N/10mm	≥3	≥2	≥2
CD	IEC-626-2	N/10mm	≥2	≥2	≥2
Humidity content	IEC-626-2	%	0.1	0.1	0.1
Breakdown voltage	IEC-626-2	kV	≥5	≥7	≥12

Trademark information: Flexiso® is a registered trademark of Dr. Dietrich Müller GmbH, Germany.

Information:

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Dr. Dietrich Müller GmbH makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Dr. Dietrich Müller GmbH only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Dr. Dietrich Müller GmbH be liable for any incidental, indirect or consequential damages arising from the sale, resale, use, or misuse of the product. Dr. Dietrich Müller GmbH Specifications are subject to change without notice. In addition, Dr. Dietrich Müller GmbH reserves the right to make changes in materials or processing without notification to the Buyer, which do not affect compliance with any applicable specification.

Dr. Dietrich Müller GmbH