

Electrical insulating materials

Flexiso® RPRG FI 13060

Composition: Flexiso® RPRG FI 13060 is a three-ply insulation material made of polyester film and pressboard on both sides. Flexiso® RPRG FI 13060 is used in insulation class B (130 °C).

Property: Flexiso® RPRG FI 13060 has a pressboard ply which has a good impregnation with impregnating and trickle resins of all insulation classes and characterizes by good bonding to all winding components. Furthermore Flexiso® RPRG FI 13060 has a smooth surface and can be processed very good. Additionally Flexiso® RPRG FI 13060 has a grained surface and therefore it is very flexible.

Applications: Flexiso® RPRG FI 13060 is used as layer insulation for coil end and phase insulations.

Form of supply: Flexiso® RPRG FI 13060 is supplied on rolls (up to ca. 1260 mm), as reels (with a width from 4 mm) and also as feathered reels. Further formats, cuts, die-cut or formed parts are manufactured according to customer request, for example self-adhered.

Storage conditions: Flexiso® RPRG FI 13060 can be stored unlimited under normal conditions (20°C, 50% rel. air humidity) in the original packaging. The material should be protected against humidity, dryness and direct sun- und UV-radiation as well as heat influence.

Dr. Dietrich Müller GmbH

Flexiso® RPRG FI 13060

Property	Test method	Unit	Value	
Nominal thickness before graining	IEC 641	mm	0.15	0.25
Nominal thickness after graining	IEC 641	mm	0.41	0.54
Film thickness		μ	23	23
Area weight	IEC 641	g/m ²	180 ± 12%	330 ± 12%
Yield	IEC 641	m ² /kg	5.6	3.0
Standard sleeve	IEC 641	mm	70	70
Tensile strength				
MD	IEC 641	N/mm ²	≥90	≥190
CD	IEC 641	N/mm ²	≥70	≥140
Elongation				
MD	IEC 641	N/10mm	≥3.0	≥5.0
CD	IEC 641	N/10mm	≥13.0	≥13.0
Dielectric strength	IEC 641	kV/mm	≥5.0	≥5.0
Shrinkage				
MD	IEC 641	%	≤0.7	≤0.7
CD			≤1.0	≤1.0
Moisture content	IEC 641	%	≤6	≤7

Trademark information: Flexiso® is a registered trademark of the Dr Dietrich Müller GmbH, Germany.

Please note:

The information in this data sheet is based on our current knowledge and experience. They do not disengage the fabricator and user from own tests and inspections because of the plenty of possible effects. There is no judicial binding assurance of certain properties or of the qualification for a concrete application in our declaration. We recommend consulting us in individual cases. The acceptor of our products has to observe possible industrial property rights as well as present laws by himself.

Dr. Dietrich Müller GmbH